

CutSpec™ for GreenIce Cure system:

Product: IceStart & IceStop

Basic Use: *Surface Applied Supplementary Cementitious Material Admixture, the first treatment of a two-part Surface Applied Admixture Cure and Densification System.*

For comprehensive manufacturer instructions, visit <https://greenumbrellasystems.com/greenice-cure/>

IceStart™ & IceStop™ is a concrete cure system designed for Interior or Exterior concrete with a polished concrete sheen—by Green Umbrella® of Rochester, NY (844) 200-7336 R.T.U. (Ready to Use), S.O.L.O. (Spray-On, Leave-On). Green Umbrella IceStart™ is a *Surface Applied Supplementary Cementitious Material Admixture, the first treatment of a two-part Surface Applied Admixture Cure and Densification System*. Used only on *@EarlyAge* concrete, IceStart™ is a chemical and mechanical process applied during concrete placement and power troweling. 1) Apply IceStart™ during screeding or bull-floating, prior to breaking open the substrate using pans, @1200 SF per gallon. 2) Next, spray IceStart™ onto the slab in two equal applications of 1200 SF per gallon during initial panning and initial troweling for three total applications with a net coverage rate of 400 SF per gallon. Use a low-pressure, high-volume manual or battery-powered commercial sprayer. Alternatively, a screed mounted unit, and the retardant tanks of ride-on power trowels may be used. Always apply sufficient material for total net coverage of 400 SF per gallon. 3) Work into the surface following second and third applications during power troweling. 4) After the final application of IceStart™, trowel burn as desired. When the concrete is hard enough for walking, apply Green Umbrella IceStop™, a Hydro-phobic *Fixative for Surface Applied Admixture Cure, the second treatment of a two-part Surface Applied Admixture Cure* 5) A single S.O.L.O. application of 400 SF per gallon. Keep wet for a dwell time of 30 minutes. Allow to air dry. No cure & seal, concrete hardener, or wet cure is needed. Apply IceStart™ and IceStop™ only when temperatures are 40°F and rising, not exceeding 90°F.

For full CSI specifications: <https://greenumbrellasystems.com/specifications/>

Contact Technical Sales: info@greenumbrellasystems.com